

https://dspace.org/

Phosphide capacities of ferromanganese smelting slags

Maramba, Blessing

2008-04-21T05:28:34Z
http://hdl.handle.net/10539/4767

Downloaded from a DSpace repository. https://dspace.org/

PHOSPHIDE CAPACITIES OF FERROMANGANESE SMELTING SLAGS

Blessing Maramba

A dissertation submitted to the Faculty of Engineering, University of the Witwatersrand, Johannesburg, in fulfillment of the requirements for the degree of Master of Science in Engineering.

Johannesburg, February 2007

DECLARATION

I declare that this dissertation is my own, unaided work. It is being submitted for the Degree of Master of Science in the University of the Witwatersrand, Johannesburg. It has not been submitted before for any degree or examination in any other University.

_____

(Signature of candidate)

_____ day of _____ 2007

ABSTRACT

Factors influencing the equilibrium phosphorous distribution, Lp, and phosphide capacity, C_P^{3-}, of ferromanganese smelting slags in highly reducing atmospheres were studied in this research work at 1500^{o}C (1773^{o}K). The research work seeks to extend the concept of slag capacities to submerged electric arc furnace operations used in the production of ferromanganese alloys. The concept of slag capacities has been used fairly widely in the steelmaking industry particularly in ladle technology processes to control various impurities including sulphur and phosphorous.

Equilibrium experimental runs were conducted in graphite crucibles under two different atmospheres, CO and Ar/CO mixture at 1500^{o}C. The resultant partial pressure of oxygen in the two atmospheres was 1.223×10^{-16}atm. and 7.826×10^{-19} atm. respectively at 1500^{o}C. The compositions of the slag samples were determined using the extreme vertices design method for mixture experiments. The composition of ferromanganese slag samples was in the following range, MnO 5-10 wt. %, SiO_2 36-54 wt. %, CaO 18-36 wt. %, P_2O_5 1-4 wt. %, and Al_2O_3 and MgO were fixed at 5 wt. % and 10 wt. % respectively. Three types of alloy samples were made and their composition was in the following range Mn 70-85 wt. %, Fe 6-18 wt. %, Si 1.5-4.5 wt. % and C was fixed at 7.5 wt. %.

The analytical results of the final equilibrium slag and metal samples were used to calculate the equilibrium phosphorous distribution ratios, Lp, and these were used in turn to calculate the slag C_P^{3-}. The results for Lp, and C_P^{3-}, were further used to derive empirical models to predict Lp and C_P^{3-} as functions of slag composition using statistical modeling. Graphs were compiled to determine the effect of varying the slag composition on Lp and C_P^{3-} parameters. Increasing the SiO_2 content in the slag reduced slag basicity which led to a decrease of the slag Lp and C_P^{3-} parameters. Increasing the slag basicity under both atmospheres led to an increase of both Lp and C_P^{3-}. Increasing slag CaO content, a basic oxide, led to an increase in both Lp and

C_P^{3-} parameters of the slag. The ferromanganese slag Lp and C_P^{3-} parameters decreased with a reduction of Po_2 in the controlling atmosphere. Therefore an overall increase in slag basicity resulted in an increase of Lp and Cp^{3-} under both atmospheres. An overall decrease in slag basicity resulted in a decrease of Lp and Cp^{3-}.

To Nyasha, Taonga and Tafadzwa for their support and patience.

ACKNOWLEDGEMENTS

The author acknowledges the financial support by FerroAlloy Producers Association of South Africa (FAPA), the Mellon Foundation and Wits University without their support this work could not be completed. The author also expresses great appreciation to Prof R. H. Eric and Prof Kuccukaragoz without their support and guidance this work would not have been successful. Last but not least great acknowledgements to all the staff members in the School of Chemical and Metallurgical Engineering who helped me at various stages of this research work.

CONTENTS **Page**

DECLARATION ii
ABSTRACT iii
DEDICATION v
ACKNOWLEDGEMENTS vi
CONTENTS vii
LIST OF FIGURES xi
LIST OF TABLES xvii

1 INTRODUCTION 1

1.1 Manganese Ore Production in South Africa 1
1.2 Uses of Manganese and Ferromanganese Production 1
1.3 Ferroalloy Usage in Steelmaking and the Associated Sulphur and Phosphorus Problems 3
1.4 Project Motivation 6

2 LITERATURE REVIEW 8

2.1 Partitioning of Phosphorus in the Blast Furnace 8
2.2 Phosphorus Removal in Steelmaking Processes 9
2.2.1 The Basic Open-Hearth process – the flush-slag practice 9
2.2.2 The removal of phosphorus in top blown oxygen steelmaking processes 10
2.2.3 Phosphorus removal in bottom blown oxygen steelmaking processes (Basic Bessemer process) 11

2.3 The Removal of Phosphorus from the Metal Phase 15
2.3.1 Equilibrium conditions 15
2.3.2 The effect of oxygen potential, temperature and slag basicity on dephosphorisation 18
2.3.3 The activities of phosphorus in the metal and in the slag 20
2.3.4 Ionic and empirical treatments of phosphorus partitioning 22
2.3.5 Reversion of phosphorus into the metal during casting 23
2.4 Basicity in Metallurgical Slags 24
2.4.1 The optical basicity concept 26
2.4.2 Effect of slag basicity 27
2.5 Evaluation of Slag-Metal Equilibrium 28
2.5.1 Oxygen equilibrium 28
2.5.2 Activities of metal phase components 29
2.5.3 Activities of oxides in the slag 30
2.6 Slag Systems for Dephosphorisation 30
2.6.1 The distribution of phosphorus between Na_2O-SiO_2-$PO_{2.5}$ melts and carbon saturated iron 30
2.6.2 Thermodynamics of phosphate and phosphide in CaO-CaF_2 melts 35
2.6.3 Dephosphorisation equilibria between liquid iron and highly basic CaO-based slags saturated with MgO 43
2.6.4 Fluospar slags used in ferrous ladle metallurgy 51
2.7 Determination of Phosphide Capacities in Smelting Slags 52
2.7.1 Equilibrium considerations 55
2.7.2 Determination of phosphide capacities of ferromanganese slags 58

2.8 Physico-Chemical Properties of Slags Associated with the Production of High Carbon Ferromanganese 60
2.8.1 Slag composition and properties 62
2.8.2 Furnace operation 63
2.9 Optimum Slag – Alloy Relationships for the Production of Medium to Low Carbon Ferromanganese 64
2.10 The Equilibrium Distribution of Elements Between the Metal and Slag Phases with Temperature at Carbon Saturation Condition 67

3 EXPERIMENTAL TECHNIQUE AND PROCEDURE 69

3.1 Experimental Set-up 69
3.1.1 Furnace assembly 69
3.1.2 Gas purification train and gas flow control 73
3.1.3 Temperature control and temperature profile 74
3.2 Statistical Experimental Design 75
3.3 Sample Preparation 79
3.3.1 High carbon ferromanganese slag samples 79
3.3.2 High carbon ferromanganese metal samples 82
3.4 Determination of the Equilibrium Time 82
3.5 Crucible Production 83
3.6 Gas-Slag-Metal Equilibrium Experimental Procedure 83
3.6.1 Conditions for the gas-slag-metal equilibrium experiments 84
3.6.2 Equilibrium relationships investigated 85
3.7 Chemical Analysis 85

4 RESULTS AND DISCUSSION 86

4.1 Gas-Slag-Metal Equilibrium 86
4.1.1 Relationships for slag-metal equilibrium under carbon monoxide atmosphere at 1500°C 96
4.1.2 Relationships for slag-metal equilibrium under Ar/ CO atmosphere at 1500°C 110
4.1.3 Comparison of the relationships for slag-metal equilibrium under carbon monoxide atmosphere to argon/carbon monoxide mix atmosphere at 1500°C 123

5 CONCLUSIONS AND RECOMMENDATIONS 127

5.1 Summary and Conclusion 127
5.2 Recommendations for Future Work 129

APPENDIX A LISTING OF EXPERIMENTAL RESULTS 130
APPENDIX B DETERMINATION OF THE ACTIVITY COEFFICIENT OF PHOSPHOROUS IN THE FERROMANGANESE 143
APPENDIX C THE COMPOSITION OF GASES USED AND KEY TO SYMBOLS USED IN SECTION 3 144
APPENDIX D DETERMINATION OF EXPERIMENTAL DESIGN POINTS DESIGNATIONS IN THE MIXTURE MODEL 145
APPENDIX E CALCULATION OF THE PREVAILING PARTIAL PRESSURE OF OXYGEN IN THE REACTION TUBE 151
APPENDIX F CALCULATION OF *X* THE EQUIVALENT CATION FRACTION 154

REFERENCES 155

LIST OF FIGURES

Figure		Page
2.1	Change of metal composition with time in the "Basic Bessemer process"	14
2.2	Comparison of the oxygen potentials at which phosphorus can transfer from the metal to slag with the oxygen potentials of various iron and steel making processes	19
2.3	The relationship between phosphorus distribution ratio and slag basicity $X_{Na_2O}/\left(X_{SiO_2}+X_{PO_{2.5}}\right)$ at 1200°C	33
2.4	A comparison of phosphate capacities of various systems	34
2.5	$(\%PO_4^{3-})/(P_{P_2}^{1/2})$ and $(\%P^{3-})/(P_{P_2}^{1/2})$ in the $CaO_{(sat)}$-CaF_2 melt as a function of Log Po_2	40
2.6	Phosphate and phosphide capacities against wt. % CaO for the CaO-CaF_2 system	41
2.7	Stability of phosphate and phosphide ions for the CaO-CaF_2 system saturated with CaO as a function of log Po_2	42
2.8	Phosphorus distribution ratios as a function of wt. % (FeO_n)	48
2.9	The relationship between $(\log C_{PO_4^{3-}})$ and mole fraction of FeO_n (X_{FeOn})	49
2.10	Relation between the optical basicity, Λ and $\log C_{PO_4^{3-}}$ for highly basic slags at 1600°C	50
2.11	Phosphide-phosphate solubilities in a calcium aluminate slag	54
2.12	Schematic diagram of electric furnace showing zone of incipient fusion	61
2.13	Variation of slag and metal composition with temperature at carbon saturation condition	68
3.1	Flow diagram of experimental set-up	71

Figure		Page
3.2	A cross section of the vertical molybdenum wound resistance furnace	72
4.1	The variation of (a) Lp and (b) C_p^{3-} with silica (X_{SiO2}) in $MnO-SiO_2-Al_2O_3-MgO-P_2O_5-CaO$ slag under CO atmosphere at 1500°C; Basicity (B): 0.8778 – 0.8897; CaO and MgO were restricted to a narrow range	101
4.2	The variation of Lp The variation of (a) Lp and (b) C_p^{3-} with silica (X_{SiO2}) in $MnO-SiO_2-Al_2O_3-MgO-P_2O_5-CaO$ slag under CO atmosphere at 1500°C; B: 0.547 – 0.725; MnO and MgO were limited to a narrow range	102
4.3	The variation of (a) Lp and (b) C_p^{3-} with $MnO-SiO_2-Al_2O_3-MgO-P_2O_5-CaO$ slag basicity (B) under CO atmosphere at 1500°C; MnO and MgO were limited to a narrow range	103
4.4	The variation of (a) Lp and (b) C_p^{3-} with $MnO-SiO_2-Al_2O_3-MgO-P_2O_5-CaO$ slag basicity (B) under CO atmosphere at 1500°C; MnO and MgO were kept to a narrow range.	104
4.5	The variation of (a) Lp and (b) C_p^{3-} with calcium oxide (X_{CaO2}) in $MnO-SiO_2-Al_2O_3-MgO-P_2O_5-CaO$ slag under CO atmosphere at 1500°C; Basicity (B): 0.6222 – 0.727; CaO and SiO_2 were restricted to a narrow range	105
4.6	The variation of (a) Lp and (b) C_p^{3-} with calcium oxide (X_{CaO}) in $MnO-SiO_2-Al_2O_3-MgO-P_2O_5-CaO$ slag under CO atmosphere at 1500°C; Basicity (B): 1.0516 – 1.083; CaO and MgO were restricted to a narrow range	106
4.7	The variation of Lp (a) The variation of (a) Lp and (b) C_p^{3-} with magnesium oxide (X_{MgO}) in $MnO-SiO_2-Al_2O_3-MgO-P_2O_5-CaO$ slag under CO atmosphere at 1500°C; Basicity (B): 0.650 – 1.059; SiO_2 and MgO were restricted to a narrow range.	107

Figure		Page
4.8	The variation of (a) Lp and (b) C_p^{3-} with manganese oxide (X_{MnO}) in MnO-SiO_2-Al_2O_3-MgO-P_2O_5-CaO slag under CO atmosphere at 1500°C; Basicity (B): 1.0516 – 1.0990; CaO and MgO were restricted to a narrow range	108
4.9	The variation of (a) Lp and (b) C_p^{3-} with manganese oxide (X_{MnO}) in MnO-SiO_2-Al_2O_3-MgO-P_2O_5-CaO slag under CO atmosphere at 1500°C; Basicity (B): 0.5897 – 0.8925; SiO_2 and MgO were restricted to a narrow range	109
4.10	The variation of (a) Lp and (b) C_p^{3-} with silica (X_{SiO2}) in MnO-SiO_2-Al_2O_3-MgO-P_2O_5-CaO slag under Ar/ CO atmosphere at 1500°C; Basicity (B): 1.1839 – 1.2498; SiO_2 and MnO were kept to a narrow range	113
4.11	The variation of (a) Lp and (b) C_p^{3-} with silica (X_{SiO2}) in MnO-SiO_2-Al_2O_3-MgO-P_2O_5-CaO slag under Ar/ CO atmosphere at 1500°C; Basicity (B): 1.0274 – 1.1041; SiO_2 and MnO were kept to a narrow range	114
4.12	The variation of (a) Lp and (b) Cp with MnO-SiO_2-Al_2O_3-MgO -P_2O_5-CaO slag basicity (B) under Ar/ CO atmosphere at 1500°C; B: 1.0273 – 1.1041; SiO_2 and MnO were kept to a narrow range	115
4.13	The variation of (a) Lp and (b) Cp with MnO-SiO_2-Al_2O_3-MgO -P_2O_5-CaO slag basicity (B) under Ar/ CO atmosphere at 1500°C; B: 1.2482 – 1.2498; SiO_2 and MnO were kept to a narrow range.	116
4.14	The variation of (a) Lp and (b) C_P^{3-} with calcium oxide (X_{CaO}) in MnO-SiO_2-Al_2O_3-MgO-P_2O_5-CaO slag under Ar/CO atmosphere at 1500°C; Basicity (B): 1.0273 – 1.0970; MnO and MgO were kept to a narrow range	117

Figure		Page
4.15	The variation of (a) Lp and (b) C_P^{3-} with calcium oxide (X_{CaO}) in $MnO-SiO_2-Al_2O_3-MgO-P_2O_5-CaO$ slag under Ar/CO atmosphere at 1500°C; Basicity (B): 1.1774 – 1.2571; MnO and SiO_2 were restricted to a narrow range.	118
4.16	The variation of (a) Lp and (b) C_P^{3-} with magnesium oxide (X_{MgO}) in $MnO-SiO_2-Al_2O_3-MgO-P_2O_5-CaO$ slag under Ar/CO atmosphere at 1500°C; Basicity B: 1.1362 – 1.2571; SiO_2 and MgO were restricted to a narrow range	119
4.17	The variation of (a) Lp and (b) C_P^{3-} with magnesium oxide (X_{MgO}) in $MnO-SiO_2-Al_2O_3-MgO-P_2O_5-CaO$ slag under Ar/CO atmosphere at 1500°C; Basicity (B): 1.0229 – 1.2498; MnO and MgO were restricted to a narrow range.	120
4.18	The variation of (a) Lp and (b) C_P^{3-} with manganese oxide (X_{MnO}) in $MnO-SiO_2-Al_2O_3-MgO-P_2O_5-CaO$ slag under Ar/ CO atmosphere at 1500°C; Basicity (B): 1.1040 – 1.2498; MnO and SiO_2 were restricted to a narrow range.	121
4.19	The variation of (a) Lp and (b) C_P^{3-} with manganese oxide (X_{MnO}) in $MnO-SiO_2-Al_2O_3-MgO-P_2O_5-CaO$ slag under Ar/ CO atmosphere at 1500°C; Basicity (B): 1.1674 – 1.3544; MnO and SiO_2 were restricted to a narrow range.	122
4.20	Comparison of the variation of (a) Lp and (b) C_P^{3-} with silica (X_{SiO2}) in $MnO-SiO_2-Al_2O_3-MgO-P_2O_5-CaO$ slag under CO atmosphere vs Ar/CO atmosphere at 1500°C; Basicity (B): 1.1040 – 1.2498; MnO and SiO_2 were restricted to a narrow range.	124
4.21	Comparison of the variation of (a) Lp and (b) C_P^{3-} with $MnO-SiO_2-Al_2O_3-MgO-P_2O_5-CaO$ slag basicity (B) under CO atmosphere compared to Ar/CO atmosphere at 1500°C	125

Figure		Page
4.22	Comparison of the variation of (a) Lp and (b) C_P^{3-} with calcium oxide (X_{CaO}) in MnO-SiO_2-Al_2O_3-MgO-P_2O_5-CaO slag under CO atmosphere compared to Ar/CO atmosphere at 1500^oC	126
A1	The variation of (a) Lp and (b) C_P^{3-} with silica (X_{SiO2}) in MnO-SiO_2-Al_2O_3-MgO-P_2O_5-CaO slag under CO atmosphere at 1500^oC; Basicity (B): 1.0671 – 1.083; MnO and SiO_2 were restricted to a narrow range	130
A2	The variation of Lp (a) and Cp (b) with (MnO-SiO_2-Al_2O_3-MgO -P_2O_5-CaO) slag basicity (B) under CO atmosphere at 1500^oC, MnO and MgO were kept to a narrow range	131
A3	The variation of (a) Lp and (b) C_P^{3-} with silica (X_{SiO2}) in MnO-SiO_2-Al_2O_3-MgO-P_2O_5-CaO slag under CO atmosphere at 1500^oC; Basicity (B): 1.0671 – 1.083; MnO and SiO_2 were restricted to a narrow range	132
A4	The variation of (a) Lp and (b) C_P^{3-} with manganese oxide (X_{MnO}) in MnO-SiO_2-Al_2O_3-MgO-P_2O_5-CaO slag under CO atmosphere at 1500^oC, Basicity (B): 0.8942 – 0.9862; MnO and MgO were kept to a narrow range	133
A5	The variation of (a) Lp and (b) C_P^{3-} with silica (X_{SiO2}) in MnO-SiO_2-Al_2O_3-MgO-P_2O_5-CaO slag under Ar/ CO atmosphere at 1500^oC, Basicity (B): 1.2004 - 1.1362, SiO_2 and MgO were kept to a narrow range	134
A6	The variation of (a) Lp and (b) C_p^{3-} with MnO-SiO_2-Al_2O_3-MgO-P_2O_5-CaO slag basicity (B) under Ar/CO atmosphere at 1500^oC; MgO and SiO_2 were kept to a narrow range	135
A7	The variation of (a) Lp and (b) C_P^{3-} with MnO-SiO_2-Al_2O_3-MgO-P_2O_5-CaO slag basicity (B) under Ar/CO atmosphere at 1500^oC; SiO_2 and MnO were kept to a narrow range	136

Figure		Page
A8	The variation of (a) Lp and (b) C_P^{3-} with calcium oxide (X_{CaO}) in $MnO-SiO_2-Al_2O_3-MgO-P_2O_5-CaO$ slag under Ar/CO atmosphere at 1500°C, Basicity (B): 1.1040 – 1.2346; MnO and MgO were kept to a narrow range	137
A9	The variation of (a) Lp and (b) C_P^{3-} with calcium oxide (X_{CaO}) in $MnO-SiO_2-Al_2O_3-MgO-P_2O_5-CaO$ slag under Ar/CO atmosphere at 1500°C, Basicity (B): 1.2354 – 1.3517; MnO and MgO were restricted to a narrow range	138
A10	The variation of (a) Lp and (b) C_P^{3-} with magnesium oxide (X_{MgO}) in $MnO-SiO_2-Al_2O_3-MgO-P_2O_5-CaO$ slag under Ar/CO atmosphere at 1500°C, Basicity (B): 1.2354 – 1.2445; SiO_2 and MnO were restricted to a narrow range	139
A11	The variation of (a) Lp and (b) C_P^{3-} with magnesium oxide (X_{MgO}) in $MnO-SiO_2-Al_2O_3-MgO-P_2O_5-CaO$ slag under Ar/CO atmosphere at 1500°C, Basicity (B): 1.3310 – 1.3469; SiO_2 and MnO were restricted to a narrow range	140
A12	The variation of (a) Lp and (b) C_P^{3-} with magnesium oxide (X_{MgO}) in $MnO-SiO_2-Al_2O_3-MgO-P_2O_5-CaO$ slag under Ar/CO atmosphere at 1500°C, Basicity (B): 1.0969 – 1.2814; MgO and MnO were restricted to a narrow range	141
A13	The variation of (a) Lp and (b) C_P^{3-} with magnesium oxide (X_{MnO}) in $MnO-SiO_2-Al_2O_3-MgO-P_2O_5-CaO$ slag under Ar/CO atmosphere at 1500°C, Basicity (B): 1.1839 – 1.2019; SiO_2 and MgO were restricted to a narrow range	142

LIST OF TABLES

Table		Page
1.1	The typical composition of Ferromanganese alloys	2
1.2	The composition ranges for the manganese oxide slags	3
3.1	Ferromanganese slag composition range	75
3.2	Coordinates of the 17 selected design points for the FeMn slag composition in the defined constraint region	77
3.3	Composition of HC-FeMn master slags (wt. %)	80
3.4	Composition of the final slag samples for HC-FeMn equilibrium experiments (wt. %)	81
3.5	The composition of HC-FeMn alloy samples for use in the equilibrium experiments (wt %)	82
4.1	Chemical analysis of the final equilibrium slag samples in CO gas atmosphere experiments (wt. %)	88
4.2	Chemical analysis results for the final equilibrium slag samples in CO gas atmosphere experiments	89
4.3	Chemical analysis results for the final equilibrium metal samples in CO atmosphere experiments (wt. %)	90
4.4	Chemical analysis results for the final equilibrium slag samples in Ar/CO gas atmosphere experiments (wt. %)	91
4.5	Chemical analysis results for the final equilibrium slag samples in Ar/CO gas atmosphere experiments	92
4.6	Chemical analysis results for the final equilibrium metal samples in Ar/ CO atmosphere experiments (wt. %)	93
4.7	Correlation coefficients for the quadratic response surface models for the equilibrium phosphorus distribution ratio (Lp) and the phosphide capacity (Cp) for ferromanganese slags	95

Table		Page
B1	Interaction coefficients of phosphorous	143
C1	Chemical composition of CO and Ar gases	144
C2	Key to symbols used in the tables with initial sample compositions	144
D1	Ferromanganese slag composition range	145
D2	Lower boundary (a_i) and Upper boundary (b_i) conditions for the four variable factors	145
D3	All the possible combinations of (q – 1) factors	146
D4	Treatment combinations for the FeMn slag composition in the defined constraint region with four variable factors	148
D5	Coordinates of the 21 design points for the FeMn slag composition in the defined constraint region	150